



# Wild

Glazed porcelain tiles



Scan to learn more



Size 7<sup>3</sup>/<sub>4</sub>" x 39<sup>3</sup>/<sub>8</sub>"

Thickness  $\pm$  8 mm

Finish Matte

V4 SUBSTANTIAL VARIATION



Field tiles	Commercial size (in)	Nominal size (in)	Thickness (mm)	Finish	Edge
	8" x 40"	7 <sup>3</sup> / <sub>4</sub> " x 39 <sup>3</sup> / <sub>8</sub> "	8 mm	Matte	Calibrated

Please refer to caliber chart for working size. Close joints are not recommended.

Property	Test Method	Requirements			
		Calibrated	Rectified		
<b>Regularity characteristics</b> 	<b>Nominal Size</b>		$\pm 3.00\%$	$-3.00\% \div +2.00\%$	Compliant
	<b>Caliber Range</b>	ASTM C499	$\pm 0.50\%$ or $\pm 0.08$ in ( $\pm 2.0$ mm) (*)	$\pm 0.25\%$ or $\pm 0.03$ in ( $\pm 0.8$ mm) (*)	Compliant
	<b>Thickness<sup>(1)</sup></b>		Range: 0.04 in (1.02 mm)		Compliant
	<b>Wedging</b>	ASTM C502	$\pm 0.50\%$ or $\pm 0.08$ in ( $\pm 2.0$ mm) (*)	$\pm 0.25\%$ or $\pm 0.03$ in ( $\pm 0.8$ mm) (*)	Compliant
	<b>Warpage Edge</b>	ASTM C485	$\pm 0.75\%$ or $\pm 0.09$ in ( $\pm 2.3$ mm) (*)	$\pm 0.40\%$ or $\pm 0.05$ in ( $\pm 1.3$ mm) (*)	Compliant
	<b>Warpage Diagonal</b>	ASTM C485	$\pm 0.50\%$ or $\pm 0.08$ in ( $\pm 2.0$ mm) (*)	$\pm 0.40\%$ or $\pm 0.07$ in ( $\pm 1.8$ mm) (*)	Compliant
<b>Structural characteristics</b>	<b>Water Absorption</b>	ASTM C373	$\leq 0.5\%$		$\leq 0.5\%$
<b>Bulk mechanical characteristics</b>	<b>Breaking Strength</b>	ASTM C648	Average $\geq 250$ lbf. (1.11 kN) Individual $\geq 225$ lbf. (1.00 kN)		$\geq 350$ lbf. avg
<b>Physical properties</b>	<b>Bond Strength</b>	ASTM C482	$\geq 50$ psi. (0.34 Mpa)		$\geq 100$ psi.
<b>Thermal and hygrometric characteristics</b>	<b>Resistance to Freeze/Thaw Cycling</b>	ASTM C1026			Resistant
	<b>Thermal Shock Resistance</b>	ASTM C484			Resistant
<b>Chemical characteristics</b>	<b>Chemical Resistance</b>	ASTM C650			Unaffected
	<b>Stain Resistance</b>	ASTM C1378			Unaffected
<b>Safety characteristics</b>	<b>Dynamic Coefficient of Friction (DCOF)</b>	ANSI A326.3	Subject to the project <sup>(2)</sup> <sup>(3)</sup>		$\geq 0.42$ Wet Interior Wet (IW) <sup>(2)</sup>

(\*) Whichever is less.

(1) Whichever is less, for tiles up to 24"x24" (610 mm x 610 mm).

(2) DCOF  $\geq 0.42$  Wet may not be a requirement for all projects.

(3) The specifier shall determine tiles appropriate for specific project conditions, considering by way of example, but not in limitation, type of use, traffic, expected contaminants, expected maintenance, expected wear, and manufacturers' guidelines and recommendations. For updated manufacturer classification according to ANSI A326.3. Section 4 - "Product Use Categories", please refer to our website.

For more details please see the catalogue or visit [atlasconcordeusa.com](http://atlasconcordeusa.com)  
The Health Product Declaration® logo is a registered trademark of HPD Collaborative.

